



## Technical Data Sheet

### QUALIX-RCA

In cooling down after dyeing Qualix-RCA has an excellent reduction clear effect and is very suitable for removing unfixed coloring material from polyester, viscose cellulose acetate and natural silk it simultaneously decolorizes the dye bath

#### Technical Literature

|                   |   |                                                                               |
|-------------------|---|-------------------------------------------------------------------------------|
| Nature            | : | Soda fused organic acid derivative aqueous solution                           |
| Physical Form     | : | Viscous pale color solution                                                   |
| Recommended Use:  |   | The doses of Qualix-RCA depends on the depth of shade of dyeing to be treated |
| Storage Stability | : | one year in closed sealed container                                           |

#### Recipe

Prior to add the Qualix-RCA to the bath pH should be acidic take hydrochloric acid (HCL)

For medium depth of shade : 1.0-1.5

For deep shade : 1.5-2.5

Hold for 20 minutes at 80°C and rinsed the fabric with fresh water after treatment of fabric having cellulose acetate the doses of Qualix-RCA will higher and temperature should not exceed more than 60°C.

## Quality Chem

*Manufacturer, Importers & Exporters*

-----ISO 9001:2000 Certified Company-----

U-22, Yash Shopping Center, Opp. Jivan Jyot Cinema, Udhna, Surat, Gujarat 394210  
e-mail: [info@hytechsurat.com](mailto:info@hytechsurat.com) Ph: (0261) 2275866, Mo: 98252 91596/ 9377090700  
work: prabhuvandana Compound, Opp. Dhruv Motors Udhna, Surat